

Technical Report Documentation Page

1. REPORT No.

CA-TL-78-19

2. GOVERNMENT ACCESSION No.

3. RECIPIENT'S CATALOG No.

4. TITLE AND SUBTITLE

The Effect of Pavement Grooving On Skid Resistance

5. REPORT DATE

June 1978

6. PERFORMING ORGANIZATION

7. AUTHOR(S)

B.D. Murray

8. PERFORMING ORGANIZATION REPORT No.

9. PERFORMING ORGANIZATION NAME AND ADDRESS

State of California
Department of Transportation
Division of Construction
Office of Transportation Laboratory

10. WORK UNIT No.

11. CONTRACT OR GRANT No.

12. SPONSORING AGENCY NAME AND ADDRESS

13. TYPE OF REPORT & PERIOD COVERED

Final Report

14. SPONSORING AGENCY CODE

15. SUPPLEMENTARY NOTES

16. ABSTRACT

Introduction

California has been grooving concrete pavements since the early 1960's to prevent accidents. A 1972 study (1) indicated that grooving certain sections of roadway has yielded in a two year period a:

1. 20 percent reduction in total accidents
2. 50 percent reduction in fatal accidents
3. 70 percent reduction in wet pavement accidents

These results were based on thirty-nine roadway locations that had been grooved. It must be recognized that one of the reasons for selecting the locations to be grooved was that these pavements exhibited high wet weather accident rates.

17. KEYWORDS

TL No. 641139B

18. No. OF PAGES:

14


19. DRI WEBSITE LINK

<http://www.dot.ca.gov/hq/research/researchreports/1978-1980/78-19.pdf>

20. FILE NAME

78-19.pdf

THE EFFECT OF PAVEMENT GROOVING ON SKID RESISTANCE



FINAL REPORT
JUNE 1978

Caltrans
CALIFORNIA DEPARTMENT OF TRANSPORTATION

NOTICE

The contents of this report reflect the views of the Office of Transportation Laboratory which is responsible for the facts and the accuracy of the data presented herein. The contents do not necessarily reflect the official views or policies of the State of California. This report does not constitute a standard, specification, or regulation.

The State of California does not endorse products or manufacturers. Trade or manufacturer's names appear herein only because they are considered essential to the object of this document.

STATE OF CALIFORNIA
DEPARTMENT OF TRANSPORTATION
DIVISION OF CONSTRUCTION
OFFICE OF TRANSPORTATION LABORATORY

June 1978

TL No. 641139B

Mr. C. E. Forbes
Chief Engineer


Dear Sir:

I have approved and now submit for your information this final research project report titled:

THE EFFECT OF PAVEMENT GROOVING
ON SKID RESISTANCE

Study made by Roadbed & Concrete
Under the Supervision of D. L. Spellman
Principal Investigator J. A. Matthews
Co-Investigator B. D. Murray
Report Prepared by B. D. Murray

Very truly yours,



GEORGE A. HILL
Chief, Office of Transportation Laboratory

Attachment

BDM:1b

SECRET

CONFIDENTIAL

CONFIDENTIAL

CONFIDENTIAL

INTRODUCTION

California has been grooving concrete pavements since the early 1960's to prevent accidents. A 1972 study (1) indicated that grooving certain sections of roadway has yielded in a two year period a:

1. 20 percent reduction in total accidents
2. 50 percent reduction in fatal accidents
3. 70 percent reduction in wet pavement accidents

These results were based on thirty-nine roadway locations that had been grooved. It must be recognized that one of the reasons for selecting the locations to be grooved was that these pavements exhibited high wet weather accident rates.

DISCUSSION

Grooving is considered most beneficial in reducing accidents, as it increases lateral control of vehicles which is often more important than stopping distance. Grooving is also effective in reducing hydroplaning which can induce skidding accidents. It has been well established that grooving has reduced accidents due to the reasons cited above; however, the effect of grooving on the skid resistance measured parallel to the direction of grooving using the Standard ASTM Towed Trailer has not been extensively examined and reported on.

The purpose of this work was to perform an overall analysis of skid test results from numerous pavements which have been grooved. Four hundred and fifty-seven test sections were located on twelve different highway routes throughout the State which had been tested for skid resistance prior to and following grooving. The

Camomiled
PLOVER BOMBA

25% COTTON FIBRE

115 A

data was evaluated using a diagonal regression procedure based on least squares linear regression analysis principles applied to variables that are not free of error. This diagonal regression line can be obtained using the equation:

$$\frac{Y-m_y}{\sigma_y} = \frac{X-m_x}{\sigma_x}$$

where m_y , m_x are the means and σ_y^2 and σ_x^2 the variances of y and x respectively.

Basically this method yields that regression line which can be visualized as obtained by performing two linear regression analyses. The first analysis the "before" grooving skid numbers are treated as dependent variables and the "after" grooving skid numbers as independent variables. The second analysis requires treating the "before" grooving skid numbers as the independent variables and the "after" grooving skid numbers as the dependent variables. The regression line obtained in the first analysis is plotted using routine procedures. The regression line obtained from the second analysis is plotted with the $x - y$ axis reversed. It is noted that these two lines cross at the mean point for both before and after grooving skid numbers. The small angle between the two regression lines is then bisected in proportion to the estimated standard deviations of the "before" and "after" skid number data and the correlation line constructed.

Using the aforementioned statistical method the data was evaluated in three separate groupings. The first group represented the northern half of the state while the second group represented the southern half of the state. The data was then combined into the third group and evaluated as representative of the entire state. The difference between the north and south state is not significant

and as such a statewide relationship can be used. The final linear correlation line for the combined north/south state group is presented in Figure 1.

This relationship indicates that on the average the skid number increases from three to five points when a pavement is grooved, with the greater increase corresponding to those pavements with the higher skid numbers prior to grooving. On a percentage basis the higher skid number pavements prior to grooving, increase approximately 8% to 10% with grooving. Those pavement with low skid numbers prior to grooving generally increase 14% to 16% in skid number with grooving.


The aforementioned results are averages and just that. One estimated standard deviation about the correlation line is 5.85 skid number points. As an example 95% of the pavement with a "before" grooving skid number of 30 will have an "after" grooving skid number in the approximate range of 22 to 46 with an average of 34.

CONCLUSIONS

In summary, skid tests made parallel to the grooving do not reflect the improvement in lateral control. Skid numbers as measured by the ASTM Towed Trailer do not show any dramatic changes in longitudinal skid resistance parallel to traffic following grooving. The average skid resistance measurements can vary more due to seasonal variations in the traffic contaminants (road grime, oil, agricultural products) present on the pavements than that from grooving. It appears that grooves ground parallel to traffic, only slightly improved longitudinal skid resistance and as such should not be used solely for improving longitudinal skid resistance. In many cases it is the loss of lateral control that appears to be a dominant cause of skidding accidents (one car accidents, for example) as compared to "rear-end" type collisions.

Handwritten text, possibly a signature or name, located in the upper right quadrant of the page.

FIGURE 1.



FLOWER POWER

AMERICAN

USA

Communist

REFERENCE

1. "A Study of the Effects of Grooving on Motor Vehicle Accidents", James A. Moe, Director of Public Works, January 1972.

Cambridge
FLOWER BOND
MULTIFIBER
USA